

# ALPHA<sup>®</sup> ROSIN FLUX 800 (RF-800)

No Clean Flux

## DESCRIPTION

**ALPHA RF-800** provides the broadest process window for a no-clean flux with less than 5% solids content. **ALPHA RF-800** is designed to provide excellent soldering results (low defects rates), even when the surfaces to be soldered (component leads and pads) are not highly solderable. **ALPHA RF-800** works particularly well with bare copper boards protected with organic or rosin/resin coatings and with tin-lead coated PCB's. **ALPHA RF-800** is used successfully in both tin-lead and lead-free applications.

**ALPHA RF-800** is a very active, low solid, no-clean flux. It is formulated with a proprietary activator system. A small percentage of rosin is added for enhanced thermal stability. The activators are designed to provide the broadest operating window for a low solid, no-clean flux, while maintaining a high level of long-term electrical reliability. After wave soldering, **ALPHA RF-800** leaves a low level of non-tacky residue, which is easily penetrable in pin testing.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

## FEATURES & BENEFITS

- Highly active for excellent soldering and low defect rates.
- Low level of non-tacky residue to reduce interference with pin testing.
- Cleaning is not required which reduces operating costs.
- Reduces the surface tension between solder mask & solder to significantly reduce solder ball frequency.
- Meets Bellcore requirements for long-term electrical reliability.

**APPLICATION GUIDELINES**

**Preparation** - In order to maintain consistent soldering performance and electrical reliability, it is important to begin the process with circuit boards and components that meet established requirements for solderability and ionic cleanliness. It is suggested that assemblers establish specifications on these items with their suppliers and that suppliers provide Certificates of Analysis with shipments and/or assemblers perform incoming inspection. A common specification for the ionic cleanliness of incoming boards and components is 5µg/in<sup>2</sup> maximum, as measured by an Omegameter with heated solution.

Care should be taken in handling the circuit boards throughout the process. Boards should always be held at the edges. The use of clean, lint-free gloves is also recommended. When switching from one flux to another, the use of a new foam stone is recommended (for foam fluxing).

Conveyors, fingers and pallets should be cleaned. ALPHA SM-110 Solvent Cleaner has been found to be very useful for these cleaning applications. When foam fluxing, do not use hot fixtures or pallets. Hot fixtures/pallets will deteriorate the foam head.

**Flux Application** – ALPHA RF-800 is formulated to be applied by foam, wave or spray methods. When foam fluxing, the foam fluxer should be supplied with compressed air which is free of oil and water.

Keep the flux tank full at all times. The flux level should be maintained 1 inch to 1-½ inches above the top of the stone. Adjust the air pressure to produce the optimum foam height with a fine, uniform foam head.

A uniform coating of flux is essential to successful soldering. When using the foam or wave method of application, an air knife is recommended after the fluxing operation. An air knife will help ensure that the flux is uniformly distributed across the board and will remove the excess flux. When spray fluxing, the uniformity of the coating can be visually checked by running a piece of cardboard over the spray fluxer or by processing a board-sized piece of tempered glass through the spray and then through the preheat section.

| Operating Parameter                                                                                                                                                                                                                                                                                                                                                                                                                         | Sac305/Sacx0307                                                                                                      | 63sn/37pb                                                                                                   |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------|
| Amount of Flux Applied                                                                                                                                                                                                                                                                                                                                                                                                                      | Single Wave:<br>1000 to 1200 µg/in <sup>2</sup> of solids<br>Dual Wave:<br>1100 to 1500 µg/in <sup>2</sup> of solids | Foam:<br>1,000 to 2,000 µg/in <sup>2</sup> of solids<br>Spray:<br>750 to 1,500 µg/in <sup>2</sup> of solids |
| <b>When foam fluxing</b>                                                                                                                                                                                                                                                                                                                                                                                                                    |                                                                                                                      |                                                                                                             |
| Foam Stone Pore Size                                                                                                                                                                                                                                                                                                                                                                                                                        | 20 to 50 µm                                                                                                          | 20 to 50 µm                                                                                                 |
| Distance that top of stone is submerged below flux                                                                                                                                                                                                                                                                                                                                                                                          | 1 to 1½ inches (25 to 40 mm)                                                                                         | 1 to 1½ inches (25 to 40 mm)                                                                                |
| Foam Fluxer Chimney Opening                                                                                                                                                                                                                                                                                                                                                                                                                 | 3/8 to 1/2 inch (10 to 13 mm)                                                                                        | 3/8 to 1/2 inch (10 to 13 mm)                                                                               |
| <b>When foam fluxing, use an Air Knife</b>                                                                                                                                                                                                                                                                                                                                                                                                  |                                                                                                                      |                                                                                                             |
| Air Knife Hole Diameter                                                                                                                                                                                                                                                                                                                                                                                                                     | 1 to 1.5 mm                                                                                                          | 1 to 1.5 mm                                                                                                 |
| Distance Between Holes                                                                                                                                                                                                                                                                                                                                                                                                                      | 4 to 5 mm                                                                                                            | 4 to 5 mm                                                                                                   |
| Distance from Fluxer to Air Knife                                                                                                                                                                                                                                                                                                                                                                                                           | 4 to 6 inches (10 to 15 cm)                                                                                          | 4 to 6 inches (10 to 15 cm)                                                                                 |
| Air Knife Angle Back toward Fluxer from Perpendicular                                                                                                                                                                                                                                                                                                                                                                                       | 3 to 5°                                                                                                              | 3 to 5°                                                                                                     |
| Topside Preheat Temperature                                                                                                                                                                                                                                                                                                                                                                                                                 | 190 to 247 °F (85 to 120 °C)                                                                                         | 190 to 230 °F (85 to 110 °C)                                                                                |
| Bottomside Preheat Temperature                                                                                                                                                                                                                                                                                                                                                                                                              | about 65 °F (35 °C)<br>higher than topside                                                                           | about 65 °F (35 °C)<br>higher than topside                                                                  |
| Maximum Ramp Rate of Topside Temperature (to avoid component damage)                                                                                                                                                                                                                                                                                                                                                                        | 2 °C/second (3.5 °F/second)<br>maximum                                                                               | 2 °C/second (3.5 °F/second)<br>maximum                                                                      |
| Conveyor Angle                                                                                                                                                                                                                                                                                                                                                                                                                              | 5 to 8° (6° most common)                                                                                             | 5 to 8° (6° most common)                                                                                    |
| Conveyor Speed                                                                                                                                                                                                                                                                                                                                                                                                                              | 3 to 6 feet/minute<br>(.9 to 1.8 meters/minute)                                                                      | 4 to 6 feet/minute<br>(1.2 to 1.8 meters/minute)                                                            |
| Contact Time in the Solder (includes ChipWave and Primary Wave)                                                                                                                                                                                                                                                                                                                                                                             | 1.5 to 3.5 seconds<br>(2 to 2½ seconds most common)                                                                  | 1.5 to 3.5 seconds<br>(2 to 2½ seconds most common)                                                         |
| Solder Pot Temperature                                                                                                                                                                                                                                                                                                                                                                                                                      | 490 to 520 °F (250 to 270 °C)                                                                                        | 460 to 500 °F (235 to 260 °C)                                                                               |
| These are general guidelines which have proven to yield excellent results; however, depending upon your equipment, components, and circuit boards, your optimal settings may be different. In order to optimize your process, it is recommended to perform a designed experiment, optimizing the most important variables (amount of flux applied, conveyor speed, preheat temperatures, and solder pot temperature and board orientation). |                                                                                                                      |                                                                                                             |

**Flux Solids Control** - If foam, wave, or rotary drum, spray fluxing, the flux solids will need to be controlled via thinner addition to replace evaporative losses of the flux solvent. As with any flux with less than 5% solids content, specific gravity is not an effective measurement for assessing and controlling the solids content. Monitoring and controlling the acid number is recommended for maintaining the solids content. The acid number should be controlled to between 17 and 19. Alpha's Flux Solids Control Kit #3, a digital titrator, is suggested. Request Alpha's Technical Bulletin SM-458 for details on the kit and titration procedure. When operating the foam fluxer continuously, the acid number should be checked every two to four hours. Over time, debris and contaminants will accumulate in recirculating type flux applicators. For consistent soldering performance, dispose of spent flux every 40 hours of operation. After emptying the flux, the reservoir and foam stone should be thoroughly cleaned with flux thinner.

**Residue Removal** – ALPHA RF-800 is a no-clean flux and the residues are designed to be left on the board. However, if desired, ALPHA RF-800 residues can be removed with ALPHA 2110 Saponifier.

**Touch-Up/Rework** - Use of the Cleanline Write Flux Applicator with ALPHA NR205 flux and ALPHA Telecore Series cored solder wire is recommended for hand soldering applications.

#### TECHNICAL DATA

| Parameters                       | Typical Values      | Parameters/Test Method                    | Typical Values                  |
|----------------------------------|---------------------|-------------------------------------------|---------------------------------|
| Appearance                       | Pale, yellow liquid | pH (5% aqueous solution)                  | 3.4                             |
| Solids Content, %wt/wt           | 4.1                 | Recommended Thinner                       | <b>ALPHA 425</b>                |
| Acid Number (mg KOH/g)           | 18.0 ± 1.0          | Shelf Life (from Date of Mfg.)            | 540 days                        |
| Specific Gravity @ 25 °C (77 °F) | 0.794 ± 0.003       | Container Size Availability               | 1, 5, and 55 Gallons; 20 Liters |
| Pounds Per Gallon                | 6.6                 | Bellcore TR-NWT-000078, Issue 3 Compliant | Yes                             |
| Flash Point (T.C.C.)             | 56 °F (13 °C)       | IPC J-STD-004 Designation                 | ROL0                            |

**CORROSION & ELECTRICAL TESTING – SAC305 ALLOY**
**Corrosion Testing**

| Corrosion Testing          | Requirement                   | Results               |
|----------------------------|-------------------------------|-----------------------|
| Silver Chromate Paper Test | No Detection of Halide        | PASS                  |
| Copper Mirror Test         | No Complete Removal of Copper | PASS                  |
| IPC Copper Corrosion Test  | No evidence of corrosion      | No Corrosion (Type L) |

**IPC J-STD-004A Surface Insulation Resistance**

| Test                                                                                                         | Conditions           | Requirements               | Results                     |
|--------------------------------------------------------------------------------------------------------------|----------------------|----------------------------|-----------------------------|
| "Comb-Down" Un-cleaned                                                                                       | 85 °C/85% RH, 7 days | $> 1.0 \times 10^8 \Omega$ | $1.1 \times 10^{10} \Omega$ |
| "Comb-Up" Un-cleaned                                                                                         | 85 °C/85% RH, 7 days | $> 1.0 \times 10^8 \Omega$ | $9.8 \times 10^9 \Omega$    |
| Control Boards                                                                                               | 85 °C/85% RH, 7 days | $> 1.0 \times 10^9 \Omega$ | $1.1 \times 10^{10} \Omega$ |
| IPC Test Condition (per J-STD-004A): -50V, measurement @ 100V/IPC B-24 board (0.4 mm lines, 0.5 mm spacing). |                      |                            |                             |

**Bellcore Surface Insulation Resistance**

| Test                                                                                                            | Conditions           | Requirements                  | Results                     |
|-----------------------------------------------------------------------------------------------------------------|----------------------|-------------------------------|-----------------------------|
| "Comb-Down" Un-cleaned                                                                                          | 35 °C/85% RH, 4 days | $> 1.0 \times 10^{11} \Omega$ | $7.0 \times 10^{13} \Omega$ |
| "Comb-Up" Un-cleaned                                                                                            | 35 °C/85% RH, 4 days | $> 1.0 \times 10^{11} \Omega$ | $4.6 \times 10^{13} \Omega$ |
| Control Boards                                                                                                  | 35 °C/85% RH, 4 days | $> 2.0 \times 10^{11} \Omega$ | $3.1 \times 10^{13} \Omega$ |
| Bellcore Test Condition (per TR-NW T-000078, Issue 3: 48 Volts, measurement @ 100V/25 mil lines/50 mil spacing. |                      |                               |                             |

**Bellcore Electrochemical Migration Resistance**

| Test                                                                                                                                                      | SIR (Initial)     | SIR (Final)       | Requirement                      | Result | Visual Result |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------|-------------------|----------------------------------|--------|---------------|
| "Comb-Up" Un-cleaned                                                                                                                                      | $3.0 \times 10^9$ | $3.8 \times 10^9$ | SIR (Initial)/SIR (Final) $< 10$ | PASS   | PASS          |
| "Comb-Down" Un-cleaned                                                                                                                                    | $2.8 \times 10^9$ | $4.0 \times 10^9$ | SIR (Initial)/SIR (Final) $< 10$ | PASS   | PASS          |
| Bellcore Test Condition (per TR-NW T-000078, Issue 3): 85°C/85%RH/500 Hours/10V, measurement @ 100V/IPC B-25 B Pattern (12.5 mil lines, 12.5 mil spacing) |                   |                   |                                  |        |               |

## RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area.



## SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

## CONTACT INFORMATION

[www.macdermidalpha.com](http://www.macdermidalpha.com)

|                                                                                         |                                                                                                                   |                                                                                                                      |
|-----------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------|
| <b>North America</b><br>140 Centennial Avenue<br>Piscataway, NJ 08854<br>1.800.367.5460 | <b>Europe</b><br>Unit 2, Genesis Business Park<br>Albert Drive<br>Woking, Surrey, GU21 5RW, UK<br>44.01483.758400 | <b>Asia</b><br>8/F., Two Sky Parc<br>51 Hung To Road<br>Kwun Tong, Kowloon,<br>Hong Kong, SAR China<br>852.2500.5365 |
|-----------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------|

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.